

Brinell (10mm/500kg)	Vickers (Diamond)	Rockwell F (1/16")	Rockwell E (1/8")	Webster (Model B)	Barcol GYZ- 9341)
45	46	36	47	5	60
50	51	46	55	7	63
55	56	54	62	9	66
60	61	61	68	10	68
65	66	67	72	11	70-73
70	71	71	77	12	75
75	76	76	80	13-14	76
80	82	79	83	14-15	77
85	87	82	86	15	79
90	92	85	88	15-16	80
95	98	87	90	16	82
100	103	89	92	16-17	83
105	109	91	94	17	84
110	115		96		

Disclaimer:

The information contained herein is provided for general guidance only. We make no representations or warranties, express or implied, regarding the accuracy, completeness, or suitability of this information, and shall have no liability for any actions taken or decisions made in reliance on it. Where required by a specification, tensile properties must always be established using recognized tensile testing procedures.